



<b>Model:</b>	<b>Topping-R Nata</b>
<b>Size:</b>	<b>32 x 99cm</b>
<b>Thickness:</b>	<b>11mm</b>
<b>Material type:</b>	<b>White Body</b>
<b>Group:</b>	<b>Bill annex L</b>

## TECHNICAL DATA

Manufacture process	Single-firing	Dry pressed ceramic tile
Length, width, thickness, side straightness, ortogonality, flatness	Conforms to the requisites applicable to each model as defined in standard UNE-EN 14411	UNE EN ISO 10545 Part 2
Water absorption	E > 10%	UNE EN ISO 10545 Part 3
Flexion resistance (N/mm.2) y and breaking strength (N)	> 15 > 600	UNE EN ISO 10545 Part 4
Lineal thermic dilatation	< 7*10 <sup>-6</sup> /°C	UNE EN ISO 10545 Part 8
Thermic impact resistance	Stands the test	UNE EN ISO 10545 Part 9
Expansion due to moisture	< 0.6%	UNE EN ISO 10545 Part 10
Cracking resistance	Stands the test	UNE EN ISO 10545 Part 11

## CHEMICAL RESISTANCE

Domestic cleaning products	Class GA	
Swimming pool salt	Class GA	UNE EN ISO 10545 Part 13
Acids and bases (low concentration)	Minimum Class GLB	
Stains resistance	Minimum Class 4	UNE EN ISO 10545 Part 14